



Infrastructure Technologies

Materials Science & Engineering, 37 Graham Road (PO Box 56), Highett, Victoria 3190, Australia
Telephone: 61 3 9252 6000 Facsimile: 61 3 9252 6244 Email: tiles@csiro.au Web: <http://www.cmse.csiro.au>
ABN 41 687 119 230

Registered Testing Authority - CSIRO

7 December 2015

Our Ref: EN13 / 1135 03/0211

TEST REPORT No. 7236

Requested by: Wet-seal
on (date): 19 November 2014
Product Descriptions: Wet-seal GS 211 Below ground Waterproof Membrane /Fabric system
Batch Number GS 29 24 30 AX (Olive)
Manufacturer: UREKA
Sampling Details
Date: 19 November 2014
How (methods): Delivered to Highett

While CSIRO takes care in preparing the reports it provides to clients, it does not warrant that the information in this particular report will be free of errors or omissions or that it will be suitable for the client's purposes. CSIRO will not be responsible for the results or any actions taken by the client or any other person on the basis of the information contained in the report or any opinions expressed in it.

The reproduction of this test report is only authorised in the form of a complete photographic facsimile. Our written approval is necessary for any partial reproduction.

This test report consists of 4 pages.

SUMMARY OF ASSESSMENTS REPORTED

AS/NZS 4858:2004	Appendix A, Durability of waterproof membranes	Pass
AS/NZS 4858:2004	Appendix B, Resistance of Waterproofing Membranes to Cyclic Movement	Pass
AS 3558.-1999	Water Absorption	1.99%
ASTM E96	Moisture Vapour Transmission	Pass

TERM OF VALIDITY

This CSIRO wet area membrane report will lapse three years after the initial date of issue and assessment unless revalidation has been requested and granted.

The validity date for report 7236 is 7 December 2017



REPORT NO: 7236 Page 2 of 4
ISSUE DATE: 7 December 2014
MANUFACTURER: WET-SEAL
PRODUCT DESC: Wet-seal GS 211 Below ground Waterproof Membrane /Fabric system

SUMMARY OF RESULTS

AS4858:2004 Wet Area Membranes

Appendix A: Assessment of Durability of waterproof membranes

The sample requires an elongation at break strain percentage greater than 34% at 56 days.
Note: (34% equates to 50% of control elongation at break strain percentage).

Durability of membranes: Elongation to break Strain %.

Report No.	6129.2A	7236	
Control	68%	74%	Class II
Water Immersion	67%		PASS
Detergent Immersion	67%		PASS
Bleach Immersion	73%		PASS
Heat Ageing - 50 °C	71%		PASS

WET-SEAL test sample, Wet-seal GS 211 Below ground Waterproof Membrane /Fabric system achieves the performance requirements of AS/NZS 4858: 2004 Durability of Membranes for Class II membrane installation.

Appendix B: Assessment of resistance of waterproofing membranes to cyclic movement

Class II type membrane: 2mm gauge length for a 0.34mm extension, repeated 50 cycles.

Requirement: No fatigue cracking exhibited.

Result: **PASS**

The Water Vapour Transmission (WVT) in accordance to ASTM E96: 0.78g/m²/24h

Appendix C: Suitability of waterproofing membranes when used over particle board

Appendix C will not be required as the Wet-seal GS 211 Below ground Waterproof Membrane /Fabric system has a water vapour transmission below 8g/m²/24h.

AS 3558.1 Methods of testing plastics & composite materials sanitary plumbing fixtures:

Method 1: Determination of water absorption characteristics

Water absorption:	Sample 1	1.99%	
	Sample 2	1.77%	
	Sample 3	1.37%	Maximum 1.99%

Conclusion: Wet-seal GS 211 Below ground Waterproof Membrane /Fabric system does not require a 'Suitability over particleboard' to pass the requirements of AS/NZS 4858 Wet area membranes.



Infrastructure Technologies

Materials Science & Engineering, 37 Graham Road (PO Box 56), Highett, Victoria 3190, Australia

Telephone: 61 3 9252 6000 Facsimile: 61 3 9252 6244 Email: tiles@csiro.au Web: <http://www.cmse.csiro.au>

ABN 41 687 119 230

REPORT NO: 7236 Page 3 of 4
ISSUE DATE: 7 December 2014
MANUFACTURER: WET-SEAL
PRODUCT DESC: Wet-seal GS 211 Below ground Waterproof Membrane /Fabric system

TEST CARRIED OUT IN ACCORDANCE WITH AS4858:2004 Wet Area Membranes Test Date: 2 December 2014
Appendix A: Assessment of Durability of waterproof membranes

RESULTS: Location: Ceramic Tile Laboratory
Conditions: 7 days at 23°C 55%RH
Sample Number: 7236 - 1 (Numbered 1 to 5)
Samples: Average of 5 samples
Load rate: 150mm/min

Elongation at Break

CONTROL SET

Sample Number	Sample Thickness Mean (mm)	Maximum Load (N)	Maximum Extension (mm)	Maximum Stress MPa	Maximum Strain %
7236 – 1 1 to 5	1.01	31.95	24.40	5.18	74

Requirement for Class II: The specimens have an average percentage strain of $\geq 60\%$ & $\leq 299\%$.

Classification: Class II (Medium extensibility)



Infrastructure Technologies

Materials Science & Engineering, 37 Graham Road (PO Box 56), Highett, Victoria 3190, Australia

Telephone: 61 3 9252 6000 Facsimile: 61 3 9252 6244 Email: tiles@csiro.au Web: <http://www.cmse.csiro.au>

ABN 41 687 119 230

REPORT NO: 7236 Page 4 of 4
ISSUE DATE: 7 December 2014
MANUFACTURER: WET-SEAL
PRODUCT DESC: Wet-seal GS 211 Below ground Waterproof Membrane /Fabric system

Date and Place 7 December 2014 Highett, Vic

Name, Title and Signature:



ANDY GIANG
TECHNICAL OFFICER

SLIPS, SURFACES & FINISHES
INDUSTRIAL RESEARCH SERVICES